

Flowchem VE SL (3 mm)



Description

A horizontal self smoothing shrinkage compensated vinyl ester resin based floor screed system with excellent chemical and mechanical resistance. Applied approx. 3mm thick.

Uses

For protection of concrete floors and bunds against aggressive chemicals, solvents and thermal attack in medium to heavy duty areas.


Benefits

- Excellent thermal resistance, up to 145°C.
- Fast curing - walk on within 12 hours.
- Excellent chemical resistance.
- Excellent abrasion and good impact resistance.
- Hygienic, - smooth and easy to clean.

Standard colour chart



Red (close to RAL 3009)



Light Grey (close to RAL 7035)




Green (close to RAL 6002)



Dark Grey (close to RAL 7046)

The applied colours may differ slightly from the examples shown above. Contact our customer services for a true colour sample.

System Design



Model Specification

Product: Flowchem VE SL

Finish: Satin matt

Thickness: 3 mm

Colour: _____

Preparatory work and application strictly in accordance with suppliers instructions.

Supplier: Flowcrete UK Ltd

Telephone : Customer Service - +44 (0) 1270 753000

Substrate Requirements

Reinforced concrete substrates should be capable of producing 1.5 N/mm² "pull-off" values and, following preparation, be free from laitance, dust and other contamination. The substrate should be visibly dry with a moisture content not exceeding 5% by weight, or 75% RH as per BS 8204, and free from rising damp and ground water pressure. If no damp proof membrane is present, use one coat of Hydraseal DPM and one coat of Flowfresh Primer directly beneath the Flowchem VE system.

Products Included in this System

Primer: Flowchem VE Primer @ 0.35 kg/m²

Topping: Flowchem VE SL @ 5.4 kg/m² for 3mm.

Note: Flowchem VE SL resin already contains Flowchem VE Topcoat Additive, so the additive should not be used in the Flowchem VE SL system.

NB: Specifications are written for each installation to meet the client's particular requirements.

Installation Service

The installation should be carried out by a Flowcrete approved contractor with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our web site www.flowcrete.com.

Note

No resin system is totally colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in very light colours but does not compromise the product's physical or chemical resistance characteristics. We have endeavoured to adopt colours within our standard range which minimise this change.

Focus on the Floorzone

Flowcrete Group plc are world leaders in specialist industrial and commercial flooring. Systems available include: underfloor heating systems, floor screeds, surface damp proof membranes, decorative floor finishes, seamless terrazzo, car park deck waterproofing, corrosion resistant systems... to name just a few.

Our objective is to satisfy your Floorzone needs.

Technical Information

The figures that follow are typical properties achieved in laboratory tests at 20°C and at 50% Relative Humidity.

Slip Resistance	Dry >40 low slip potential
Method described in BS 7976-2 (typical values for 4-S rubber slider)	(in accordance with HSE and UKSRG guidelines)

The slipperiness of flooring materials can change significantly, due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/ or surface contaminants (wet or dry).

Textured systems are recommended to meet slip resistance value requirements for wet conditions and/ or surface contaminants (wet or dry) - please contact our Technical Advisors for further details and specifications.

Temperature Resistance	145°C max. – ASTM 648.56
Chemical Resistance	See chart www.flowcrete.com
Barcol hardness	> 40 (ASTM D 2583)
E-Modulus	3.1 GPa (ASTM D 695)
Volume Shrinkage	< 0.004 % Rill 4 2.5.3.2.1
Compressive Strength	120 MPa (ASTM D 695)
Flexural Strength	100 MPa (ASTM D 790)
Tensile Strength	50 MPa (ASTM D 638)
Adhesion	> 4 MPa (Note: Substrate failure)
Density	1.85 approx.

Speed of Cure	20°C
Light traffic	12 hours
Full traffic	24 hours
Full chemical cure	72 hours

The speed of cure can be controlled by varying the accelerator dosage level. The above times are based on the standard dosage level.

Aftercare - Cleaning and Maintenance

Clean floors regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

Important Notes

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request.

Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.